

**Lower Bound on the Energy Gap at Precise Locations
on the $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ Fermi Surface**

Michael E. Flatté

Institute for Theoretical Physics

University of California

Santa Barbara, CA 93106-4030

Recent inelastic-neutron-scattering measurements of a low-energy phonon in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ provide enough information to place a lower bound on the energy gap magnitude at precise locations on the Fermi surface. Measurements of a few low-energy phonons should indicate whether the gap symmetry is $d_{x^2-y^2}$. Further measurements could map out the angle-resolved gap magnitude on the entire Fermi surface.

PACS: 74.72.Hs, 74.25.Kc, 74.25.Jb

Recently H.A. Mook, *et al.*¹, have examined the temperature-dependence of phonon linewidths in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$. The authors are primarily concerned with the behavior of high-energy phonons ($\hbar\omega > 50\text{meV}$) near and below T_c . Their results indicate strong anharmonicity and electron-phonon coupling for these modes. The purpose of this Communication is to point out that the temperature-dependence of the 5meV phonon, which was used as a control in this experiment, provides some information about the superconducting energy gap at precise locations on the Fermi surface. In previous work² I presented a method, using measurements of phonon anomalies, to determine the energy-gap anisotropy in a superconductor with a quasi-two-dimensional Fermi surface. In this Communication I will apply this method to the 5meV phonon. If the temperature-dependence of other low-energy phonons were probed, more information about the anisotropy of the gap could be obtained.

The behavior of phonon anomalies in superconductors without quasi-two-dimensional Fermi surfaces is well-known. If the superconducting gap is isotropic, the minimum energy for a phonon to decay into two quasiparticles is twice that gap. This produces an anomaly in a phonon dispersion curve at low temperature when the curve crosses $\hbar\omega = 2\Delta$, where Δ is the superconductor's gap. The anomaly also manifests itself in a temperature-shift of the phonon's linewidth across T_c (observed first³ in Nb_3Sn). When the energy gap is anisotropic, the anomaly is smoothed.

If the Fermi surface is quasi-two-dimensional, however, the anomaly remains sharp and is momentum-dependent in a useful way². The minimum energy for a phonon of wavevector $\vec{q}$ to decay into two quasiparticles in such a superconductor depends on the

gap magnitude at a discrete number of points on the Fermi surface (different for each phonon). These points can be determined by placing the phonon momentum vector on the Fermi sea such that its head and tail are located on the Fermi surface. The gap magnitude at the location of the head and the location opposite the tail determine the minimum energy according to the following equation:

$$\tilde{\Delta}(\vec{q}) \equiv |\Delta(\vec{k}_1)| + |\Delta(\vec{k}_2)|, \quad (1)$$

where $\vec{k}_1$ and $\vec{k}_2$ are the two locations on the Fermi surface described above and $\Delta(\vec{k})$ is the superconductor's gap as a function of momentum. The locations $\vec{k}_1$ and $\vec{k}_2$ are the *only* places where momentum conservation ($\vec{k}_1 + \vec{k}_2 = \vec{q}$) can be satisfied *and* low-energy excitations exist.

The minimum, or threshold energy $\tilde{\Delta}(\vec{q})$ defines a surface in energy-momentum space. The linewidths of phonons whose energies lie far above this surface should be unaffected by a transition into the superconducting state. The linewidths of phonons whose energies lie close to but above the threshold surface should increase, and those below should decrease. Information about the threshold surface can be directly inverted to obtain the gap magnitude as a function of location on the Fermi surface. Thus by observing temperature shifts in many different phonons, the gap magnitude can be mapped out everywhere on the Fermi surface.

This method has been applied² to recent data⁴ on $\text{YBa}_2\text{Cu}_3\text{O}_7$. Currently a group at Brookhaven⁵ is testing the feasibility of this theory on $\text{La}_{1.85}\text{Sr}_{0.15}\text{CuO}_4$. Preliminary results are encouraging.

The observation of the 5meV phonon changing linewidth in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ restricts the possible gap values at a few isolated points on the Fermi surface. There are three possible ways to place the phonon momentum, $[\vec{q} = 0.5(\pi, \pi)]$ on the Fermi surface (taken from photoemission data⁶) satisfying Equation (1). Vectors 1 and 2 connect points on the same piece of Fermi surface (see Figure), while vector 3 connects points on different pieces. Assuming the gap magnitude has the symmetry of the square lattice, these are the only non-degenerate ways for this phonon to decay into electronic excitations. Since the phonon is perpendicular to a line of reflection symmetry for the quasi-two-dimensional Fermi surface, $|\Delta(\vec{k}_1)| = |\Delta(\vec{k}_2)|$ for vectors 1 and 2. This places a lower bound of 2.5meV on the gap magnitude at the locations marked with filled squares and labeled 1 and 2. The Fermi surface locations probed by the vectors have been mapped by lattice symmetry to a 45° region in the first quadrant. The two squares labeled 3 correspond to vector 3, which connects two locations not identical under a lattice symmetry operation. The sum of the gap magnitudes at these points must exceed 5meV. The observation that 5meV is less than twice the gap at these locations agrees with photoemission experiments⁷.

Even though three different electronic decay channels exist for this phonon, lower bounds can be set because points 1 – 3 are very close to each other. It is conceivable, though unlikely, that the channel associated with vector 1 or 2 dominates the other two. Then the lower bound would only apply to point 1 or 2.

This complication would not affect observations of temperature shifts in some other low-energy phonons in $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$. Of particular interest would be any low-energy phonons with momenta near $0.88(\pi, 0)$. This momentum is shown on the Figure, and

marked $\vec{q}_n$. This is the only way to place the vector on the Fermi surface such that Equation (1) is satisfied. Photoemission indicates that the gap magnitudes near the head and tail of $\vec{q}_n$ are substantially smaller than elsewhere on the Fermi surface⁷. This experiment's resolution, however, is only about 10meV. Better resolution should be available with phonons.

I would like to express thanks to D.S. Dessau and Z.-X. Shen for permission to use their Fermi surface data prior to publication. This work was supported by the NSF under Grant No. PHY89-04035.

REFERENCES

- 1.. H.A. Mook, *et al.*, *Phys. Rev. Lett.* **69**, 2272, (1992).
- 2.. M.E. Flatté, *Phys. Rev. Lett.* **70**, 658, (1993).
- 3.. J.D. Axe, G. Shirane, *Phys. Rev. Lett.* **30**, 214, (1973).
- 4.. N. Pyka, *et al.*, to be published.
- 5.. H. Chou, G. Shirane, M. Matsuda, R.J. Birgeneau, to be published.
- 6.. D.S. Dessau, Z.-X. Shen, to be published.
- 7.. B.O. Wells, *et al.*, *Phys. Rev. B* **46**, 11830, (1992). Z.-X. Shen, *et al.*, unpublished.

FIGURE CAPTION

Vectors 1 – 3 are the non-degenerate ways to position the phonon momentum $\vec{q} = 0.5(\pi, \pi)$ on the $\text{Bi}_2\text{Sr}_2\text{CaCu}_2\text{O}_8$ Fermi surface (dashed line)⁶. Since the 5meV phonon narrows upon transition to the superconducting state, the gap magnitudes at locations 1 and 2 (filled squares) must exceed 2.5meV. The sum of the gap magnitudes at points 3 exceeds 5meV. Observations of linewidth changes in phonons with momenta near $\vec{q}_n$ would probe proposed nodes in the gap magnitude⁷.